

Josh's Pate de verre kiln schedule

Ramp °c/hr	Set point temp °c	Dwell hrs
30	80	3
70	600	1.5
100	710	1
999	482	3
25	427	pass
50	371	pass
100	200	pass
End		

*For objects up to approximately 12 x 12 x 12cm

*Mould thickness approximately 2cm

*Pâte de verre thickness 1-5 mm

*Bullseye glass

*Potterycrafts top loading ceramics kiln, side elements, middle shelf